

Iron Doped Biomaterial Calcium Borate: Synthesis and Characterization

G. Çelik Gül, F. Kurtuluş

Abstract—Colemanite is the most common borate mineral, and the main source of the boron required by plants, human, and earth. Transition metals exhibit optical and physical properties such as; non-linear optical character, structural diversity, thermal stability, long cycle life and luminescent radiation. The doping of colemanite with a transition metal, bring it very interesting and attractive properties which make them applicable in industry. Iron doped calcium borate was synthesized by conventional solid state method at 1200 °C for 12 h with a systematic pathway. X-ray diffraction (XRD), Fourier transform infrared (FTIR) spectroscopy, scanning electron microscopy/energy dispersive analyze (SEM/EDS) were used to characterize structural and morphological properties. Also, thermal properties were recorded by thermogravimetric-differential thermal analysis (TG/DTA).

Keywords—Colemanite, conventional synthesis, powder x-ray diffraction, borates.

I. INTRODUCTION

COLEMANITE, represented by $\text{Ca}_2\text{B}_6\text{O}_{11}\cdot 5\text{H}_2\text{O}$ simple chemical formula, contains 27.28% CaO, 50.81% B_2O_3 and 21.91% H_2O . Colemanite is crystallized in monoclinic crystal system with unit cell parameters $a=8.743 \text{ \AA}$, $b=11.264 \text{ \AA}$, $c=6.102 \text{ \AA}$, and space group P21/a [1], [2].

The “d” values of highest three intensive peaks are at 3.13, 3.85, 5.64 Å, respectively with ICDD card number 33-267 [3]. The colemanite appears colorless, white and transparent/translucent with the density of 2.42 g/cm³. The chains are extended in “a” direction in the crystal structure which formed layers of trimer borate compounds by ionic bonding with Ca ions horizontally. The layers are connected with hydrogen bonds owing to hydroxyl groups and water molecules in the chains. One $\text{BO}_2(\text{OH})$ triangle and two $\text{BO}_2(\text{OH})_2$ tetrahedral groups compose of ring form with $(\text{B}_3\text{O}_3(\text{OH})_5)^{2-}$ formula by sharing corners. Colemanite (Fig. 1) is different boron mineral by having perfect cleavage, harder structure and crystal form [4].

The DTA studies show that the water decomposition of colemanite occurs at 400 °C. The lattice changing with second endothermic reaction resulting of the formation of new crystals (forming of new lattice) are shown by the support of gradual exothermic peaks in DTA graphic. The first melting point is 960 °C; nevertheless, main melting point is about 1100 °C. However, the melt has a small amount of stable crystalline phase, the crystalline phase turns into melt utterly

G. Çelik Gül and F. Kurtuluş are with the Chemistry Department, University of Balıkesir, Balıkesir, 10145 Turkey (phone: +90-266-6121067; fax: +90-266-6121097; e-mail: gulsahcelik@balikesir.edu.tr, fdemiral@balikesir.edu.tr).

via to continue heating [5]-[8]. Colemanite has been intensively used to be a source to obtain borate compounds due to abundancy, chemically inertness, and structure containing both Ca and B atoms.

Many metal borate compounds are known as non-linear optical and laser-host material [9]. The researches about these compounds made possibility to produce laser beams with the wavelengths and power features which had not been obtained before [10]-[17].

The atomic structure of each element has a settlement layout which is specific for it; that is, the electrons in the atoms existed in a certain energy levels which has stable orbits. The electrons which are stable at their orbits get excited to upper energy level with excitement, and they come back to same energy level by leaving energy. This is the main working principle of laser [14]-[18].

Borate compounds including alkaline, alkaline earth and transition metals have some features like catalytic activity, unique magnetic behavior and high recycling in Li-ion battery [19]. Besides, the borate compounds which include rare earth metal have common usage areas which are named as phosphors [17].

The advanced side of this experimental research is obtaining of iron doped calcium borate by conventional solid state route, investigation of all structural properties for instance “d” values, crystal system, unit cell structure and unit cell parameters; moreover, colemanite is used both calcium and boron source.



Fig. 1 The crystal structure of colemanite

II. EXPERIMENTAL DETAILS

The starting materials were supplied by Riedel and Sigma companies as analytical grade. Colemanite and iron(III) oxide were weighed in three amounts of 1:1, 2:1 and 1:2. After grinding of starting materials, the samples are treated to three different temperatures 700 °C, 800 °C and 900 °C. Alls samples were characterized by X-ray powder diffraction (XRD) pattern using Panalytical X'Pert Pro Diffractometer

and Cu K_{α} radiation ($\lambda=1.54056 \text{ \AA}$, 40 mA, 50 kV). Structural properties were determined with High Score + Program and Rietveld Refinement Method.

FTIR spectra were recorded between 4000 and 600 cm^{-1} using Perkin Elmer Spectrum 100 FTIR Spectrometer. TG/DTA was carried out by Perkin Elmer Diamond TG/DTA. Morphological property and ratio of the elements of the sample were analyzed by ZEISS Supra 40 VP.

III. RESULTS AND DISCUSSION

The XRD patterns of the three systems in three temperatures are given in Fig. 2. When we compare the patterns to Inorganic Crystal Structure Database (ICSD), all

samples were corresponded to double phase Fe_2O_3 (ICSD=016-1285)/ CaB_2O_4 (ICSD=002-2060) compounds (Table I) except one sample. The Fe_2O_3 - $\text{Ca}_2\text{B}_6\text{O}_{11}\cdot 5\text{H}_2\text{O}$ system with 2:1 molar ratio at 900 °C is displayed (Table II) as pure CaB_2O_4 (ICSD=002-2060) doped with Fe^{3+} ion (Fig. 3). The absence of impurities confirms the success of doping process of calcium borate. In Table II, the calculated and observed XRD data of iron doped calcium borate can be seen with estimated “hkl” values. The unit cell structure is shown in Fig. 4 which indicates atomic positions. The unit cell parameters (Table III) are calculated by Rietveld Refinement Method using XRD data.




Fig. 2 The XRD patterns of Fe_2O_3 - CaO - B_2O_3 systems




Fig. 3 The XRD pattern of iron doped CaB_2O_4

TABLE I
MOLECULAR COMPOSITIONS OF Fe_2O_3 - CaO - B_2O_3 SYSTEMS

Fe_2O_3 - CaO - B_2O_3 systems	Synthesis temperature	Phases percentages	
		Fe_2O_3 (ICSD=016-1285)	CaB_2O_4 (ICSD=002-2060)
(a) 1 Fe_2O_3 + 1 $Ca_2B_6O_{11} \cdot 5H_2O$	700 °C	36.8	62.3
(b) 2 Fe_2O_3 + 1 $Ca_2B_6O_{11} \cdot 5H_2O$	700 °C	20.9	79.1
(c) 1 Fe_2O_3 + 2 $Ca_2B_6O_{11} \cdot 5H_2O$	700 °C	74.1	25.9
(d) 1 Fe_2O_3 + 1 $Ca_2B_6O_{11} \cdot 5H_2O$	800 °C	16.8	83.2
(e) 2 Fe_2O_3 + 1 $Ca_2B_6O_{11} \cdot 5H_2O$	800 °C	11.3	88.7
(f) 1 Fe_2O_3 + 2 $Ca_2B_6O_{11} \cdot 5H_2O$	800 °C	34.7	65.3
(g) 1 Fe_2O_3 + 1 $Ca_2B_6O_{11} \cdot 5H_2O$	900 °C	13.5	86.5
(h) 2 Fe_2O_3 + 1 $Ca_2B_6O_{11} \cdot 5H_2O$	900 °C	0.0	100.0
(I) 1 Fe_2O_3 + 2 $Ca_2B_6O_{11} \cdot 5H_2O$	900 °C	23.3	76.7




Fig. 4 Unit cell structure of iron doped CaB_2O_4

In Fig. 5, the FTIR spectrum of the sample was given. The wave numbers at 1480, 1275, 803, 706, and 633 cm^{-1} are corresponded to various vibrations of BO_3 and BO_4 groups [18]-[23]. Fig. 6 is SEM micrograph of iron doped CaB_2O_4 . The homogeneous distribution of the sample is seen in the




Fig. 5 The Infrared spectrum of iron doped CaB_2O_4

The result of EDX analyze as mass percentages of composition of iron doped calcium borate is given in Table IV. The results in the table are in a good accordance with the molar composition of calcium borate 1:2:4.

figure. The average particle size of the sample was measured in 2-5 μm .

TABLE II
OBSERVED AND CALCULATED XRD DATA OF IRON DOPED CALCIUM BORATE

$d_{obs.}$ (Å)	$d_{calc.}$ (Å)	h k l
3.3721	3.3720	1 1 1
3.1094	3.1094	0 0 2
3.0032	3.0033	1 0 2
2.8989	2.8985	4 0 0
2.8667	2.8677	3 1 0
2.7409	2.7401	2 0 2
2.6052	2.6042	3 1 1
2.4589	2.4580	1 1 2
2.4234	2.4227	3 2 0
2.2379	2.2388	4 1 1
2.1397	2.1390	0 2 0
2.1211	2.1203	4 0 2
2.0075	2.0068	2 2 0
1.9356	1.9372	5 1 1
1.8423	1.8418	1 1 3
1.6814	1.6801	3 1 3
1.6408	1.6413	6 0 2
1.5061	1.5059	4 2 2
1.5009	1.5017	2 0 4
1.3087	1.3080	3 3 1
1.2117	1.2100	9 1 1

TABLE III
UNIT CELL PARAMETERS OF IRON DOPED CALCIUM BORATE

Crystal system	Unit cell parameters		
	a (Å)	b (Å)	c (Å)
Orthorhombic	11.5953	4.2783	6.2195

The result of thermal analyze of iron doped CaB_2O_4 is given in Fig. 7. There is no significant mass loss until 1000 °C. After this temperature, a sharp mass loss starts. This mass loss which started at 1000 °C displays that the compound is quite stable in the range of 400-1000 °C.

TABLE IV
EDX RESULTS OF IRON DOPED CALCIUM BORATE

Element	Mass percentages
B	16.89
O	51.14




Fig. 6 SEM micrograph of iron doped CaB₂O₄




Fig. 7 TGA diagram of iron doped CaB₂O₄

IV. CONCLUSION

As a conclusion, iron doped calcium borate is synthesized via conventional solid state technique using iron (III) oxide and colemanite (both calcium and boron source) with 2:1 molar ratio at 900 °C by intermediate grindings. The XRD data and unit cell parameters are calculated via Rietveld Refinement Method, and infrared spectrum was measured to support functional groups.

ACKNOWLEDGMENT

We thank to TUBITAK-BIDEB and BAU-Scientific Research Project Unit for their supports.

REFERENCES

- [1] F. D. Kurtuluş, "Synthesis and characterization of metal containing borate, phosphate and borophosphate compounds by hydrothermal and microwave methods," PhD thesis, 2003, Balıkesir University, Turkey
- [2] B. Tekin, "Syntheses and structural characterization of certain compound of metal borates, phosphates and borophosphates," PhD thesis, 2007, Balıkesir University, Turkey.
- [3] R. A. Smith, R. B. Brom, "Boron compounds, oxides, acid, borates, Kirk-Othmer Encyclopedia of Chemical Technology, Wiley, New York, 1992.
- [4] R. M. Adams, "Boron, metallo-boron compounds and boranes, Wiley-Interscience, New York, 1964.
- [5] A. H. Silver, *J. Chem. Phys.*, vol. 32, pp. 959, 1960.
- [6] K. Goetzman, D. Karlheinz, N. H. Dieter, G. Ralf, Patent CA, C09K015, 1996.
- [7] Y. Zhang, J. K. Liang, X. L. Chen, M. He, T. Xu, *J. Alloys and Comp.*, vol. 327, pp. 96, 2001.
- [8] Y. Zhang, X. L. Chen, J. K. Liang, T. Xu, *J. Alloys and Comp.*, vol. 333, pp. 72, 2002.
- [9] J. L. C., Rowsell, N. J. Taylor, L. F. Nazar, *J. Solid State Chem.*, vol. 174, pp. 189, 2003.
- [10] H. Huppertz, S. Altmönshofer, and G. Heymann, "High-pressure preparation, crystal structure, and properties of the new rare-earth oxoborate β -Dy₂B₄O₉," *J. Solid State Chem.*, vol. 170, no. 2, pp. 320–329, Feb. 2003.
- [11] G. Güzel, "Synthesis of some type of lithium and boron rich chemical compounds and analyzed their structural properties by XRD," MSc. thesis, 2006, Balıkesir University, Turkey.
- [12] G. Zhang, Y. Wu, P. Fu, G. Wang, H. Liu, G. Fan, and C. Chen, "A new sodium samarium borate Na₃Sm₂(BO₃)₃," *J. Phys. Chem. Solid*, vol. 63, no. 1, pp. 145–149, Jan. 2002.

- [13] S. Lemanceau, G. C. Bertrand, R. Mahiou, M. El-Ghozzi, J. C. Coussens, P. Conflnt, and R. N. Vannier, "Synthesis and characterization of H-LnBO₃orthoborates (Ln=La, Nd, Sm, and Eu)," *J. Solid State Chem.*, vol. 148, no. 2, pp. 229–235, Dec. 1999.
- [14] S. Somunkıranoglu, "The synthesis and characterization of oxide and vanadate types of compounds containing some double metals," MSc thesis, 2014, Balıkesir University, Turkey.
- [15] Y. Shi, J. Liang, H. Zhang, J. Yang, W. Zhuang, and G. Rao, "X-Ray powder diffraction and vibrational spectra studies of rare earth borophosphates, Ln₇O₆(BO₃)(PO₄)₂(Ln=La, Nd, Gd, and Dy)," *J. Solid State Chem.*, vol. 129, no. 1, pp. 45–52, Feb. 1997.
- [16] M. Yerli, "The synthesis and characterization of some metal containing borate, phosphate and vanadate compounds," MSc. thesis, 2009, Balıkesir University, Turkey.
- [17] S. Sarıkaya Gacanođlu, "The solid state chemical synthesis and characterization studies of some new type double metal orthoborate compounds," PhD thesis, 2009, Balıkesir University, Turkey.
- [18] Y. Zhang, X. L. Chen, J. K. Liang, and T. Xu, "Synthesis and structural study of new rare earth sodium borates Na₃Ln(BO₃)₂ (Ln=Y, Gd)," *J. Alloys and Comp.*, vol. 333, no. 1–2, pp. 72–75, Feb. 2002.
- [19] M. Taşdemir, "Some theoretical applications of Rietveld analysis via GSAS computer program on powder crystal systems," MSc. thesis, 2008, Balıkesir University, Turkey.
- [20] G. Gözel, A. Baykal, M. Kızılyallı, and R. Kniep, "Optimizing the dispersion on an alumina suspension using commercial polyvalent electrolyte dispersants," *J. Europ. Ceram. Soc.*, vol. 18, no. 14, pp. 2241–2247, Dec. 1998.
- [21] K. Nakomato, *Infrared and Raman Spectra of Inorganic and Coordination Compounds*, A Willey-Interscience Publication, John Wiley and Sons, 1986.
- [22] A. Baykal, M. Kızılyallı, G. Gözel, and R. Kniep, "Synthesis of strontium borophosphate, SrBPO₅ by solid state and hydrothermal methods and characterization," *Crys. Res. Technol.*, vol. 35, no. 3, pp. 247–254, March 2000.
- [23] A. Baykal, and M. Kızılyallı, "X-ray powder diffraction and IR study of NaMg(H₂O)₂(BP₂O₈)·H₂O and NH₄Mg(H₂O)₂(BP₂O₈)·H₂O," *J. Mater. Science*, vol. 35, no. 18, pp. 4621–4626, Sep. 2000.

Gülşah Çelik Gül was born in Balıkesir, Turkey on 9th of July in 1986. She graduated from University of Uludağ, Department of Chemistry in 2008. She has a master degree of science and PhD degrees in chemistry from Balıkesir University. Her major field is inorganic chemistry.

She works as a Project Expert at Balıkesir University since 2013. She was published eleven articles in SCI-expanded journals related with inorganic chemistry and bioinorganic chemistry. Her current and previous research interests are to material science, bioinorganic chemistry, solid state chemistry, crystallography and powder X-ray diffraction.

Dr. Çelik Gül, is a member of Turkish Chemistry Society and Turkish Biochemical Society.

Figen Kurtuluş was born in Balıkesir, Turkey in 1972. She graduated from University of Uludağ Department of Chemistry Education in 1993. She has a master degree of science and PhD in chemistry from Balıkesir University. Her major field is inorganic chemistry.

She has been Prof. Dr at Balıkesir University Chemistry Department since 2016. She was published twenty articles in SCI-expanded journals related with inorganic chemistry and solid state chemistry. Her current and previous research interests are to inorganic chemistry, material science, solid state chemistry, crystallography and powder X-ray diffraction.

Prof. Dr. Kurtuluş is a member of Turkish Chemistry Society.