World Academy of Science, Engineering and Technology
International Journal of Structural and Construction Engineering
Vol:6, No:10, 2012

Influence of Atmospheric Physical Effects on Static Behavior of Building Plate Components Made of Fiber-Cement-Based Materials

Jindrich J. Melcher, and Marcela Karmazínová

Open Science Index, Structural and Construction Engineering Vol:6, No:10, 2012 publications.waset.org/3918/pdf

***Abstract*—**The paper presents the brief information on particular results of experimental study focused to the problems of behavior of structural plated components made of fiber-cement-based materials and used in building constructions, exposed to atmospheric physical effects given by the weather changes in the summer period. Weather changes represented namely by temperature and rain cause also the changes of the temperature and moisture of the investigated structural components. This can affect their static behavior that means stresses and deformations, which have been monitored as the main outputs of tests performed. Experimental verification is based on the simulation of the influence of temperature and rain using the defined procedure of warming and water sprinkling with respect to the corresponding weather conditions during summer period in the South Moravian region at the Czech Republic, for which the application of these structural components is mainly planned. Two types of components have been tested: (i) glass-fiber-concrete panels used for building façades and (ii) fiber-cement slabs used mainly for claddings, but also as a part of floor structures or lost shuttering, and so on.

***Keywords*—**Atmospheric physical effect, building component, experiment, fiber-cement, glass-fiber-concrete, simulation, static behavior, test, warming, water sprinkling, weather.

I. Introduction

THE paper authors' workplace deals with the experimental research of the actual behavior of civil structures very intensively in the long term. The experimental verification is mainly oriented to the loading tests of load-carrying structures and components, but also to other problems in the connection with load-carrying capacity, strength and resistance. Within the co-operation with the company of the Research Institute of Building Materials, Inc. (VUSTAH, a.s.) at Brno city the large research directed towards the experimental investigation of the behavior of building plate components based on fiber-cement materials has been realized recently. The attention has been paid to the development of these materials from the viewpoint of production technology, physical and chemical properties (see http://www.vustah.cz), to mechanical properties and load-carrying capacities (see mainly [1-7, 12-15]) and, last but not least, to the influence of atmospheric physical effects, caused by weather changes, on the static behavior of these products.

J. J. Melcher is with the Brno University of Technology – Faculty of Civil Engineering, 602 00 Brno, Czech Republic (phone: +420 541 147 300; fax: +420 549 245 212; e-mail: melcher.j@fce.vutbr.cz).

M. Karmazínová is with the Brno University of Technology – Faculty of Civil Engineering, 602 00 Brno, Czech Republic (phone: +420 541 147 310; fax: +420 549 245 212; e-mail: karmazinova.m@fce.vutbr.cz).

II. Principles of Test Method

The procedure of the simulation of atmospheric influences on the behavior of façade panels, oriented to the verification of temperature and rain effects on stresses and deformations of the building plate component, is based on the defined cyclic mode of the test specimen warming up and sprinkling.

To simulate the behavior of the plate structural component under warming up and sprinkling caused by varying weather conditions, an experimental conventional procedure developed at the Research Institute of Building Materials, Inc. has been utilized. The method involves producing recurrent cycles composed of partial segments:

(i) water sprinkling – 170 ± 5 min.;
(ii) pause – 10 ± 1 min.;
(iii) radiant warming up – 170 ± 5 min.;
(iv) pause – 10 ± 1 min.

In common 18 those cycles represent 1 year of component operation in the summer period upon South Moravian region.




Fig. 1 Scheme of test equipment

While warming, after the time of 15 minutes the surface temperature of 60 ± 5 ºC must be reached. The difference between the temperature in the centre and near the corners of the specimen must not be more than 15 ºC. The prescribed

Open Science Index, Structural and Construction Engineering Vol:6, No:10, 2012 publications.waset.org/3918/pdf

sprinkling intensity is 1 liter / m^2·min. The illustrative scheme of the test equipment for the procedure of the simulation "warm – rain" described above is shown in Fig. 1. The source of radiant warming is represented by the electric warm panels; sprinkling is caused by water from the sprinkling tube as a part of the sprinkling system including the tub with a pump ensuring water circulation.

The test arrangement according to the scheme in Fig. 1 is chosen with regard to fulfill the requirements corresponding to the simulation of the sun radiation and water sprinkling acting to one side of the component, which cannot be performed, for example, by testing in the closed box.

III. Glass-Fiber-Concrete Panels

A. Test Specimens

The first type of the test specimens is the building façade panel made of glass-fiber-concrete (Fig. 2) based on cement matrix reinforced by dispersed glass fibers. This material is highly resistant to the most of physical, chemical and mechanical influences (see e.g. [3, 4, 6, 8, 9, 12, 13]), but in dependence on its usage in the particular structural component the influence of moisture and temperature changes caused by atmospheric physical effects of the weather can be significant.




Fig. 2 Scheme of test specimen: glass-fiber-concrete façade panel (rotated 90º counterclockwise related to real position in construction)

In this case, in connection with atmospheric effects on the static behavior, i.a. the influence of two types of the panel anchorage to the load-carrying structure has been investigated – for anchorage detailing see e.g. Figs. 5, 6, more in [3, 4].

B. Test Arrangement and Realization

The panel warming has been realized using the system of eight electric warm sources. Sprinkling panel surface by water has been realized by the hole sprinkling tube located above the top edge of the panel and connected to the submersible pump in the tub of the testing frame. Figs. 3 to 6 illustrating test arrangement and realization demonstrate test method principle but mainly, clearly the test procedure practical application.

In total 35 cycles has been executed. The specimen surface temperature was controlled by infrared remote detectors and verified by thermo-camera (see illustration in Figs. 7 and 8).



Fig. 3 Warming glass-fiber-concrete façade panel: view to electric warm sources and water tub



Fig. 4 Warming glass-fiber-concrete façade panel: view to panel backside with installed detectors

Open Science Index, Structural and Construction Engineering Vol:6, No:10, 2012 publications.waset.org/3918/pdf



Fig. 5 Sprinkling glass-fiber-concrete façade panel: view to indicators of deformations on the side of specimen



Fig. 6 Sprinkling glass-fiber-concrete façade panel: view to water simulating rain effects

C. Test Results

The specimen has been tested 28 days after its production. At support points A, B, C, D and E, F (see scheme in Fig. 2) the characteristic forces and displacements caused by warming and water sprinkling have been measured. The basic test results are presented in Fig. 9 to 12, which show forces and deformations caused by panel shrinking or expanding as a result of temperature and moisture changes in the interaction with marginal conditions given by actual panel supporting.




Fig. 7 Illustration of thermo-camera monitoring: warming




Fig. 8 llustration of thermo-camera monitoring: coolingI

Open Science Index, Structural and Construction Engineering Vol:6, No:10, 2012 publications.waset.org/3918/pdf




Fig. 9 Resulting maximum forces in x-y plane at points A, B, C, D




Fig. 10 Maximum force at points E, F, along the z-axis




Fig. 11 Deflection at central point 3 along z-axis




Fig. 12 Entire elongation between points 1 and 2

Presented test results give verified and useful information on actual support forces and specimen displacements caused by simulated weather conditions characterized by defined procedure of warming and sprinkling of structural façade component made of glass-fiber-concrete.

IV. Fiber-Cement Slabs

A. Test Specimens

The second type of tested component is the flat slab made of fibre-cement based on cement matrix with polypropylene and cellulose fibres in a mutual combination. In comparison with glass-fibre-concrete, products made of fibre-cement do not reach such high-quality physical, chemical and mechanical properties as well as load-carrying capacity (for more see e.g. [1, 2]), but they very good complies with strict environmental and ecologic requirements.

Because of its properties, fibre-cement is usually used for the production of flat slabs applied in load-carrying structures of building and technological constructions that means, for example, lost shuttering of bridge constructions, load-carrying structures of timber ceilings and dry floors, building claddings or shuttering panels and components in the manufactures of precast concrete products.

The test specimen subjected to the sprinkling and warming up mode is made up of fiber-cement slab bolted to the vertical wooden battens of the cross-section of 80 x 50 mm (see Fig. 13), which represents, for example, the structural composition of the external wall of timber building construction.




Fig. 13 Scheme of test specimen: fiber-cement slab
(rotated 90º clockwise related to the real position in construction)

Open Science Index, Structural and Construction Engineering Vol:6, No:10, 2012 publications.waset.org/3918/pdf



Fig. 14 Installation of test specimen and test equipment for warming and sprinkling fiber-cement slab



Fig. 15 Warming fiber-cement slab: preparation of equipment



Fig. 16 Warming fiber-cement slab: view to electric warm sources



Fig. 17 Sprinkling fiber-cement slabs: view to water simulating rain effects



Fig. 18 Sprinkling fiber-cement slabs: view to water out flowing from sprinkling tube

A. Test Arrangement and Realization

The specimen warming has been realized, as in the case of glass-fiber-concrete façade panel, also by eight electric warm sources. The temperature of the specimen surface has been controlled using contactless infra-thermo-detector. For the verification of the uniform distribution and intensity of the warming upon the panel area the use of the thermo-camera can be practicable and effective.

The shots of the test arrangement and realization verifying the influence of sprinkling and warming on the structural system using fiber-cement slabs are in Figs. 13 to 18.

B. Test Results

Fig. 19 illustrates the resulting deformation of the slab (the deflection perpendicular to the centre plane [mm]) of given dimensions (see Fig. 12) after 50 cycles of the "warm-rain" mode. After the finishing total number of 50 cycles in the mode of repeated warming and water sprinkling, no obvious failures or cracks have been monitored on the surface of the tested specimen.

Open Science Index, Structural and Construction Engineering Vol:6, No:10, 2012 publications.waset.org/3918/pdf




Fig. 19 Deformations of fiber-cement slab: distribution of deflections perpendicular to centre plane (rotated 90º counter-clockwise related to the real position in construction)

V. Conclusion

Presented test results give verified and useful information on actual forces and displacements caused by simulated weather conditions characterized by defined procedure of warming and sprinkling of building structural components made of materials based on cement matrix with dispersed reinforcing fibers.

The obtained results cannot be generalized, because from particular examples mentioned above it is evident, that the results are, case by case, very different in dependence on the variability of the physical, chemical and mechanical material properties and diversity of structural detailing and supporting the components, which altogether significantly influence the component behavior caused by atmospheric effects given by weather changes.

Acknowledgment

The paper has been elaborated within the support of the solution of the research projects of the Ministry of Education, Youth and Sports MSM 0021630519 and FAST S-11-32/1252 (specific university research project).

References

[1] J. Melcher, M. Karmazínová, M. Pilgr, M. Frank, "*Defined load-carrying capacity of fibre-cements slabs" (technology, tests, tables, graphs*) (original in Czech language), VUSTAH, a.s Brno, 2011, 102 pp.

[2] J. Melcher, M. Karmazínová, "Strength characteristics of material of fiber-cement building components and verification of warming and sprinkling influence on their behavior" (original in Czech language), In *Proceedings of the XIVth International Conference on „Ecology and new building materials and products"* held in Telč, pp. 291-294, VUSTAH, a.s. Brno, 2010. ISBN 978-80-87397-02- 2.

[3] J. Melcher, M. Karmazínová, J. Knězek, L. Lederer, "The influence of physical effects on behavior of structural components made of fiber-glass-concrete" (original in Czech language), In *Proceedings of the XIth Conf. on „Ecology and new Building materials and products"* held in Telč, VUSTAH, a.s. Brno 2007, pp. 295-299. ISBN 978-80-239-9347-9.

[4] J. Melcher, M. Karmazínová, M. Knězek, L. Lederer, "Experimental verification of glass-fiber-concrete components of façade claddings" (original in Czech language), In *Proceedings of the Xth Conference on „Ecology and new building materials and products"* held in Telč, VUSTAH, a.s. Brno, 2006, pp. 347-351. ISBN 80-239-7146-8.

[5] J. Melcher, M. Karmazínová, "Loading tests of glass-fiber-concrete façade panels stiffened by rib" (original in Czech language), In *Proceedings of the IXth Conference on „Ecology and new building materials and products"* held in Telč, VUSTAH, a.s. Brno, 2005, pp. 204-208. ISBN 80-239-4905-5.

[6] M. Karmazínová, J. Melcher, R. Pokorný, P. Pospíšil, „Material characteristics of glass-fiber-concrete facade components" (original in Czech language) In *Proceedings of the VIIth Conference on "Ecology and new building materials and products*" held in Telč, VUSTAH, a.s. Brno, 2003, pp. 102-112. ISBN 80-239-1009-4.

[7] J. Melcher, M. Karmazínová, J. Knězek, "Experimental verification of glass-fiber-concrete façade panels under wind loading actions" (original in Czech language), In *Proceedings of the VIth Conference on "New building materials and products*" held in Telč, VUSTAH, a.s. Brno, 2002, pp. 52-55.

[8] M. Karmazínová, "Design assisted by testing – a powerful tool for the evaluation of material properties and design resistances from test results", In *International Journal of Mathematical Models and Methods in Applied Sciences*, Vol. 6, No. 2, 2012, pp. 376-385. ISSN 1998-0140.

[9] M. Karmazínová, M. Pilgr, J. J. Melcher, "Methods based on the approach of the design assisted by testing applied to the determination of material properties", In *Proceedings of the 2nd International Conference on Mathematical Models for Engineering Science*, Inst. of Environment, Engineering, Economics and Applied Mathematics, WSEAS Press, Puerto de la Cruz, 2011, pp. 25-30. ISBN 978-1-61804-055-8.

[10] M. Karmazínová, J. J. Melcher, "Methods of the design assisted by testing – applicable tools for the design resistance evaluation using test results", In *Proceedings of the 2nd International Conference on Mathematical Models for Engineering Science*, Institute of Environment, Engineering, Economics and Applied Mathematics, WSEAS Press, Puerto de la Cruz, 2011, pp. 31-36. ISBN 978-1-61804-055-8.

[11] M. Karmazínová, J. J. Melcher, "Design assisted by testing applied to the determination of the design resistance of steel-concrete composite columns", In *Proceedings of the 13th WSEAS International Conference on Mathematical and Computational Methods in Science and Engineering MACMESE '11*, WSEAS, Catania, 2011, pp. 420-425. ISBN 978-1-61804-046-6.

[12] J. Melcher, M. Karmazínová, J. Pozdíšek, "Experimental verification of behaviour of composite steel and glass-fibre-concrete beam", In *Proceedings of the 9th International Conference on "Steel-Concrete Composite and Hybrid Structures"* held in Leeds, Singapore: Research Publ. Services, 2009, pp. 390-395. ISBN 978-981-08-3068-7.

[13] M. Karmazínová, J. Melcher, "Possibilities of application of glass-fibre-concrete in composite steel-concrete beams", In *Proceedings of the 9th International Symposium on "Fiber-Reinforced Polymer Reinforcement for Concrete Structures"* held in Sydney, University of Adelaide, 2009, p. 51 (book) + DVD (full – 4 pp.). ISBN 978 0 9806755 0 4.

[14] ČSN EN 12467 (72 3403) "*Fibre-cement flat sheets – Product specification and test methods*" (original in Czech language) the Czech Standard Institute, Prague 2005, 48 pp.

[15] EN 1990 "*Basis of Structural Design*: *Annex D – Design assisted by testing*", CEN Brussels, 2004.