

Structural, Magnetic and Magnetocaloric Properties of Iron-Doped $\text{Nd}_{0.6}\text{Sr}_{0.4}\text{MnO}_3$ Perovskite

Authors : Ismail Al-Yahmadi, Abbasher Gismelseed, Fatma Al-Mammari, Ahmed Al-Rawas, Ali Yousif, Imaddin Al-Omari, Hisham Widatallah, Mohamed Elzain

Abstract : The influence of Fe-doping on the structural, magnetic and magnetocaloric properties of $\text{Nd}_{0.6}\text{Sr}_{0.4}\text{Fe}_x\text{Mn}_{1-x}\text{O}_3$ ($0 \leq x \leq 0.5$) were investigated. The samples were synthesized by auto-combustion Sol-Gel method. The phase purity, crystallinity, and the structural properties for all prepared samples were examined by X-ray diffraction. XRD refinement indicates that the samples are crystallized in the orthorhombic single-phase with Pnma space group. Temperature dependence of magnetization measurements under a magnetic applied field of 0.02 T reveals that the samples with ($x=0.0, 0.1, 0.2$ and 0.3) exhibit a paramagnetic (PM) to ferromagnetic (FM) transition with decreasing temperature. The Curie temperature decreased with increasing Fe content from 256 K for $x=0.0$ to 80 K for $x=0.3$ due to increasing of antiferromagnetic superexchange (SE) interaction coupling. Moreover, the magnetization as a function of applied magnetic field (M-H) curves was measured at 2 K, and 300 K. the results of such measurements confirm the temperature dependence of magnetization measurements. The magnetic entropy change $|\Delta S_M|$ was evaluated using Maxwell's relation. The maximum values of the magnetic entropy change $|\Delta S_{Max}|$ for $x=0.0, 0.1, 0.2, 0.3$ are found to be 15.35, 5.13, 3.36, 1.08 J/kg.K for an applied magnetic field of 9 T. Our result on magnetocaloric properties suggests that the parent sample $\text{Nd}_{0.6}\text{Sr}_{0.4}\text{MnO}_3$ could be a good refrigerant for low-temperature magnetic refrigeration.

Keywords : manganite perovskite, magnetocaloric effect, X-ray diffraction, relative cooling power

Conference Title : ICAMM 2019 : International Conference on Advanced Magnetocaloric Materials

Conference Location : Dublin, Ireland

Conference Dates : August 15-16, 2019