

## In-Situ Formation of Particle Reinforced Aluminium Matrix Composites by Laser Powder Bed Fusion of Fe<sub>2</sub>O<sub>3</sub>/AlSi12 Powder Mixture Using Consecutive Laser Melting+Remelting Strategy

**Authors :** Qimin Shi, Yi Sun, Constantinus Politis, Shoufeng Yang

**Abstract :** In-situ preparation of particle-reinforced aluminium matrix composites (PRAMCs) by laser powder bed fusion (LPBF) additive manufacturing is a promising strategy to strengthen traditional Al-based alloys. The laser-driven thermite reaction can be a practical mechanism to in-situ synthesize PRAMCs. However, introducing oxygen elements through adding Fe<sub>2</sub>O<sub>3</sub> makes the powder mixture highly sensitive to form porosity and Al<sub>2</sub>O<sub>3</sub> film during LPBF, bringing challenges to producing dense Al-based materials. Therefore, this work develops a processing strategy combined with consecutive high-energy laser melting scanning and low-energy laser remelting scanning to prepare PRAMCs from a Fe<sub>2</sub>O<sub>3</sub>/AlSi12 powder mixture. The powder mixture consists of 5 wt% Fe<sub>2</sub>O<sub>3</sub> and the remainder AlSi12 powder. The addition of 5 wt% Fe<sub>2</sub>O<sub>3</sub> aims to achieve balanced strength and ductility. A high relative density ( $98.2 \pm 0.55\%$ ) was successfully obtained by optimizing laser melting (Emelting) and laser remelting surface energy density (Eremelting) to  $E_{melting} = 35 \text{ J/mm}^2$  and  $E_{remelting} = 5 \text{ J/mm}^2$ . Results further reveal the necessity of increasing Emelting, to improve metal liquid's spreading/wetting by breaking up the Al<sub>2</sub>O<sub>3</sub> films surrounding the molten pools; however, the high-energy laser melting produced much porosity, including H<sub>2</sub>-, O<sub>2</sub>- and keyhole-induced pores. The subsequent low-energy laser remelting could close the resulting internal pores, backfill open gaps and smoothen solidified surfaces. As a result, the material was densified by repeating laser melting and laser remelting layer by layer. Although with two-times laser scanning, the microstructure still shows fine cellular Si networks with Al grains inside (grain size of about 370 nm) and in-situ nano-precipitates (Al<sub>2</sub>O<sub>3</sub>, Si, and Al-Fe(-Si) intermetallics). Finally, the fine microstructure, nano-structured dispersion strengthening, and high-level densification strengthened the in-situ PRAMCs, reaching yield strength of  $426 \pm 4 \text{ MPa}$  and tensile strength of  $473 \pm 6 \text{ MPa}$ . Furthermore, the results can expect to provide valuable information to process other powder mixtures with severe porosity/oxide-film formation potential, considering the evidenced contribution of laser melting/remelting strategy to densify material and obtain good mechanical properties during LPBF.

**Keywords :** densification, laser powder bed fusion, metal matrix composites, microstructures, mechanical properties

**Conference Title :** ICAMMP 2021 : International Conference on Additive Manufacturing Materials for Production

**Conference Location :** Barcelona, Spain

**Conference Dates :** December 16-17, 2021