

## Enhancing the CO<sub>2</sub> Photoreduction of SnFe<sub>2</sub>O<sub>4</sub> by Surface Modification Through Acid Treatment and Au Deposition

**Authors :** Najmul Hasan, Shiping Li, Chunli Liu

**Abstract :** The synergy effect of surface modifications using the acid treatment and noble metal (Au) deposition on the efficiency of SnFe<sub>2</sub>O<sub>4</sub> (SFO) nano-octahedron photocatalyst has been investigated. Inorganic acids (H<sub>2</sub>SO<sub>4</sub> and HNO<sub>3</sub>) were employed to compare the effects of different acids. It has been found that after corrosion treatment using H<sub>2</sub>SO<sub>4</sub> and deposition of Au nanoparticles, SnFe<sub>2</sub>O<sub>4</sub> nano-octahedron (Au-S-SFO) showed significantly enhanced photocatalytic activity under simulated light irradiation. Au-S-SFO was characterized by XRD, XPS, EDS, FTIR, Uv-vis-DRS, SEM, PL, and EIS analysis. The mechanism for CO<sub>2</sub> reduction was investigated by scavenger tests. The stability of Au-S-SFO was confirmed by continuously repeated tests followed by XRD analysis. The surface corrosion treatment of SFO octahedron with H<sub>2</sub>SO<sub>4</sub> could produce hydroxyl group (-OH) and sulfonic acid group (-SO<sub>3</sub>H) as reaction sites. These active sites not only enhanced the Au nanoparticles deposition to the acid treated SFO surface but also acted as the Brønsted acid sites that enhance the water adsorption and provide protons for CTC degradation and CO<sub>2</sub> reduction. These effects improved the carrier separation and transfer efficiency. In addition, the photocatalytic efficiency was further enhanced by the surface plasmon resonance (SPR) effect of Au nanoparticles deposited on the surface of acid-treated SFO. As a result of the synergy of both acid treatment and SPR effect from the Au NPs, Au-S-SFO exhibited the highest CO<sub>2</sub> reduction activity with 2.81, 1.92, and 2.69 times higher evolution rates for CO, CH<sub>4</sub>, and H<sub>2</sub>, respectively than that of pure SFO.

**Keywords :** surface modification, CO<sub>2</sub> reduction, Au deposition, Gas-liquid interfacial plasma

**Conference Title :** ICHPPN 2023 : International Conference on Heterogeneous Photocatalysis and Photocatalytic Nanomaterials

**Conference Location :** Zurich, Switzerland

**Conference Dates :** January 16-17, 2023