

## Structural, Optical, And Ferroelectric Properties Of BaTiO<sub>3</sub> Sintered At Different Temperatures

**Authors :** Anurag Gaur, Neha Sharma

**Abstract :** In this work, we have synthesized BaTiO<sub>3</sub> via sol gel method by sintering at different temperatures (600-1000 °C) and studied their structural, optical and ferroelectric properties through X-Ray diffraction (XRD), UV-Vis spectrophotometer and PE Loop Tracer. X-Ray diffraction patterns of barium titanate samples show that the peaks of the diffractogram are successfully indexed with the tetragonal structure of BaTiO<sub>3</sub> along with some minor impurities of BaCO<sub>3</sub>. The optical band gap calculated through UV Visible spectrophotometer varies from 4.37 to 3.80 eV for the samples sintered at 600 to 1000 °C, respectively. The particle size calculated through transmission electron microscopy varies from 20 to 60 nm for the samples sintered at 600 to 1000 °C, respectively. Moreover, it has been observed that the ferroelectricity reduces as we increase the sintering temperature.

**Keywords :** nanostructures, ferroelectricity, sol-gel method, diffractogram

**Conference Title :** ICTCME 2014 : International Conference on Textile Composites, Materials and Engineering

**Conference Location :** Melbourne, Australia

**Conference Dates :** December 16-17, 2014