

A Novel Environmentally Benign Positive Electrode Material with Improved Energy Density for Lithium Ion Batteries

Authors : Wassima El Mofid, Svetlozar Ivanov, Andreas Bund

Abstract : The increasing requirements for high power and energy lithium ion batteries have led to the development of several classes of positive electrode materials. Among those one promising material is $\text{LiNi}_x\text{Mn}_y\text{Co}_{1-x-y}\text{O}_2$ due to its high reversible capacity and remarkable cycling performance. Further structural stabilization and improved electrochemical performance of this class of cathode materials can be achieved by cationic substitution to a transition metal such as Al, Mg, Cr, etc. The current study discusses a novel NMC type material obtained by simultaneous cationic substitution of the cobalt which is a toxic element, with aluminum and iron. A compound with the composition $\text{LiNi}_{0.6}\text{Mn}_{0.2}\text{Co}_{0.15}\text{Al}_{0.025}\text{Fe}_{0.025}\text{O}_2$ (NMCAF) was synthesized by the self-combustion method using sucrose as fuel. The material has a layered $\alpha\text{-NaFeO}_2$ type structure with a good hexagonal ordering. Rietveld refinement analysis of the XRD patterns revealed a very low cationic mixing compared to the non-substituted material $\text{LiNi}_{0.6}\text{Mn}_{0.2}\text{Co}_{0.2}\text{O}_2$ suggesting a structural stabilization. Galvanostatic cycling measurements indicate improved electrochemical performance after the metal substitution. An initial discharge capacity of about 190 mAh.g^{-1} at slow rate (C/20), and a good cycling stability even at moderately faster rates (C/5 and C) have been observed. The long term cycling displayed a capacity retention of about 90% after 10 cycles.

Keywords : cationic substitution, lithium ion batteries, positive electrode material, self-combustion synthesis method

Conference Title : ICSRD 2020 : International Conference on Scientific Research and Development

Conference Location : Chicago, United States

Conference Dates : December 12-13, 2020