

Effect of Synthesis Parameters on Crystal Size and Perfection of Mordenite and Analcime

Authors : Zehui Du, Chaiwat Prapainainar, Paisan Kongkachuichay, Paweena Prapainainar

Abstract : The aim of this work was to obtain small crystalline size and high crystallinity of mordenites and analcimes, by modifying the aging time, agitation, water content, crystallization temperature and crystallization time. Two different hydrothermal methods were studied. Both methods used Na₂SiO₃ as the silica source, NaAlO₂ as the aluminum source, and NaOH as the alkali source. The first method used HMI as the template while the second method did not use the template. Mordenite crystals with spherical shape and bimodal in size of about 1 and 5 μm were obtained from the first method using conditions of 24 hr aging time, 170°C and 24 hr crystallization. Mordenites with high crystallinity were formed using agitation system in the crystallization process. It was also found that the aging time of 2 hr and 24 hr did not much affect the formation of mordenite crystals. Analcime crystals were formed in spherical shape and facet on surface with the size between 13-15 μm by the second method using the conditions of 30 minutes aging time, 170°C and 24 hr crystallization without calcination. By increasing water content, the crystallization process was slowed down and resulted in smaller analcime crystals. Larger size of analcime crystals were observed when the samples were calcined at 300°C and 580°C. Higher calcination temperature led to higher crystal growth and resulted in larger crystal size. Finally, mordenite and analcime was used as fillers in zeolite/Nafion composite membrane to solve the fuel cross over problem in direct alcohol fuel cell.

Keywords : analcime, hydrothermal synthesis, mordenite, zeolite

Conference Title : ICCE 2015 : International Conference on Chemical Engineering

Conference Location : Kyoto, Japan

Conference Dates : November 12-13, 2015