

Corrosion of Fe-(9~37) Wt%Cr Alloys at 700-800 °C in N₂-H₂O-H₂S Mixed Gas

Authors : Min Jung Kim

Abstract : Fe-(9, 19, 28, 37) wt%Cr alloys were corroded at 700 and 800 °C for 70 h under 1 atm of N₂, 1 atm of N₂/3.2%H₂O-mixed gas, and 1 atm of N₂/3.1%H₂O/2.42%H₂S-mixed gas. The corrosion rate of Fe-9Cr alloy increased with the addition of H₂O and increased further with the addition of H₂S in N₂/H₂O gas. Fe-9Cr alloy was non-protective in all gas types. In contrast, Fe-(19, 28, 37) wt%Cr alloys were protective in N₂ and N₂/H₂O-mixed gas because of the formation of the Cr₂O₃ layer. They were, however, non-protective in N₂/H₂O/H₂S-mixed gas because sulfidation dominated, forming the outer FeS layer and the inner Cr₂S₃ layer containing some FeCr₂S₄.

Keywords : Fe-(9, 19, 28, 37) wt%Cr alloys, corrosion, sulfidation, FeS

Conference Title : ICCMME 2016 : International Conference on Composite Materials and Materials Engineering

Conference Location : Tokyo, Japan

Conference Dates : May 26-27, 2016