

## Microstructure Study of Melt Spun Mg<sub>65</sub>Cu<sub>25</sub>Y<sub>10</sub>

**Authors :** Michael Regev, Shai Essel, Alexander Katz-Demyanetz

**Abstract :** Magnesium alloys are characterized by good physical properties: They exhibit high strength, are lightweight and have good damping absorption and good thermal and electrical conductivity. Amorphous magnesium alloys, moreover, exhibit higher strength, hardness and a large elastic domain in addition to having excellent corrosion resistance. These above-mentioned advantages make magnesium based metallic glasses attractive for industrial use. Among the various existing magnesium alloys, Mg<sub>65</sub>Cu<sub>25</sub>Y<sub>10</sub> alloy is known to be one of the best glass formers. In the current study, Mg<sub>65</sub>Cu<sub>25</sub>Y<sub>10</sub> ribbons were produced by melt spinning, their microstructure was investigated in its as-cast condition, after pressing under 0.5 GPa for 5 minutes under different temperatures - RT, 500C, 1000C, 1500C and 2000C - and after five minute exposure to the above temperatures without pressing. The microstructure was characterized by means of X-ray Diffraction (XRD), Differential Scanning Calorimetry (DSC), High Resolution Scanning Electron Microscope (HRSEM) and High Resolution Transmission Electron Microscopy (HRTEM). XRD and DSC studies showed that the as-cast material had an amorphous character and that the material crystallized during exposure to temperature with or without applying stress. HRTEM revealed that the as-cast Mg<sub>65</sub>Cu<sub>25</sub>Y<sub>10</sub>, although known to be one of the best glass formers, is nano-crystalline rather than amorphous. The current study casts light on the question what an amorphous alloy is and whether there is any clear borderline between amorphous and nano-crystalline alloys.

**Keywords :** metallic glass, magnesium, melt spinning, amorphous alloys

**Conference Title :** ICSRD 2020 : International Conference on Scientific Research and Development

**Conference Location :** Chicago, United States

**Conference Dates :** December 12-13, 2020