## World Academy of Science, Engineering and Technology International Journal of Materials and Metallurgical Engineering Vol:11, No:10, 2017

## Influence of Annealing on the Mechanical $\alpha c$ -Relaxation of Isotactic-Polypropylene: A Study from the Intermediate Phase Perspective

Authors: Baobao Chang, Konrad Schneider, Vogel Roland, Gert Heinrich

**Abstract :** In this work, the influence of annealing on the mechanical  $\alpha$ c-relaxation behavior of isotactic polypropylene (iPP) was investigated. The results suggest that the mechanical  $\alpha$ c-relaxation behavior depends strongly on the confinement force on the polymer chains in the intermediate phase and the thickness of the intermediate phase. After quenching at  $10^{\circ}$ C, abundant crystallites with a wide size distribution are formed. The polymer chains in the intermediate phase are constrained by the crystallites, giving rise to one broad  $\alpha$ c-relaxation peak. With an annealing temperature between  $60^{\circ}$ C ~ $105^{\circ}$ C, imperfect lamellae melting releases part of the constraint force, which reduces the conformational ordering of the polymer chains neighboring the amorphous phase. Consequently, two separate  $\alpha$ c-relaxation peaks could be observed which are labeled as  $\alpha$ c1-relaxation and  $\alpha$ c2-relaxation.  $\alpha$ c1-relaxation and  $\alpha$ c2-relaxation describe the relaxation behavior of polymer chains in the region close to the amorphous phase and the crystalline phase, respectively. Both relaxation peaks shift to a higher temperature as annealing temperature increases. With an annealing temperature higher than  $105^{\circ}$ C, the new crystalline phase is formed in the intermediate phase, which enhances the constraint force on the polymer chains.  $\alpha$ c1-relaxation peak is broadened obviously and its position shifts to a higher temperature as annealing temperature increases. Moreover,  $\alpha$ c2-relaxation is undetectable because that the polymer chains in the region between the initial crystalline phase and the newly formed crystalline phase are strongly confined.

**Keywords**: annealing, αc-relaxation, isotactic-polypropylene, intermediate phase

Conference Title: ICPCP 2017: International Conference on Polymer Chemistry and Physics

Conference Location: London, United Kingdom Conference Dates: October 19-20, 2017