Investigation of Nd-Al-Fe Added Nd-Fe-B Alloy Produced by Arc Melting

Authors : Gülten Sadullahoğlu, Baki Altuncevahir

Abstract : The scope of this study, to investigate the magnetic properties and microstructure of $Nd_2Fe_{14}B_1$ by alloying with $Nd_{33.4}Fe_{62.6}Al_4$, and heat treating it at different temperatures. The stoichiometric $Nd_2Fe_{14}B$ hard magnetic alloy and $Nd_{33.4}Fe_{62.6}Al_4$ composition was produced by arc melting under argon atmosphere. The $Nd_{33.4}Fe_{62.6}Al_4$ alloy has added to the 2:14:1 hard magnetic alloy with 48% by weight, and melted again by arc melting. Then, it was heat treated at 600, 700 and 800°C for 3h under vacuum. In AC magnetic susceptibility measurements, for the as-cast sample, the signals decreased sharply at 101 °C and 313 °C corresponding to the Curie temperatures of the two ferromagnetic phases in addition to Fe phase. For the sample annealed at 600 °C, two Curie points were observed at about 257°C and at 313°C. However, the phase corresponding to the Curie temperature of 99.8 emu/g for the sample annealed at 600 °C, and decreased to 57.66 and 28.6 emu/g for the samples annealed at 700° and 800 °C respectively. Heat treatment resulted in an evolution of the new phase that caused changes in magnetic properties of the alloys. In order to have a clear picture, the identification of these phases are being under the investigation by XRD and SEM-EDX analysis.

1

Keywords : NdFeB hard magnets, bulk magnetic materials, arc melting, Curie temperature, heat treatment

Conference Title : ICMMM 2017 : International Conference on Magnetism and Magnetic Materials

Conference Location : Barcelona, Spain

Conference Dates : August 17-18, 2017